

Fixer 9

APPLICATIONS

Increases stencil water resistance for more impressions per screen.

GENERAL CHARACTERISTICS

- Works as a catalyst with triple-cure emulsions (Ceramic HT, Textil HT, Vitrum HT) or makes a permanent, solvent-resistant and waterproof stencil
- Works as an emulsion hardener with water-resistant emulsions such as Textil DW and textil DT to make a more durable stencil.

DIRECTIONS FOR USE

Apply SaatiChem Fixer 9 thinly and evenly to both sides of the dry stencil with a sponge, brush or cloth. Remove Fixer 9 excess to avoid drips with vacuum or air jet. Allow Fixer 9 to penetrate emulsion. Then cure overnight at room temperature or for one to two hours at 122° to 140°F (50° to 60°C).

Health & Safety

Before using, refer to appropriate material safety data sheets.

STORAGE

When sealed in the original container and stored in cool conditions, SaatiChem products will maintain their original properties for one year from the date of production.

PACKAGING

Available in one and ten kilogram containers. In North America available in one quart and one gallon containers.

WARRANTY & LIMITED REMEDY

The directions, recommendations, and specifications contained in this Technical Data Sheet are meant as a guide to the use of the product and shall not bind the company. Product specifications are subject to change without notice.

The following is made in lieu of all other expressed or implied warranties, including any implied warranty of merchantability or fitness for a particular purpose:

All SaatiChem manufactured liquid products are warranted to be free of defects in materials and manufacture and to meet the specifications stated in SaatiChem's applicable Product Bulletin. SaatiChem will replace or refund the price of any SaatiChem manufactured liquid product that does not meet this warranty within the applicable warranty period.

The remedies are exclusive. In no case shall SaatiChem be liable for any other direct or indirect damage or loss, including without limitation any incidental, special, or consequential damages, or any material costs or labor charges incident to the removal or replacement of any mesh, screen, ink, substrate, finished graphic or any other item.

To receive the Material Safety Data Sheet (MSDS), send an e-mail to: MSDS@saatichem.com

USA

1.877.296.7697 [Toll-free US & Canada]
or 1.847.296.7697
e-mail: info.US@saatichem.com

Italy

+39.031.9711
e-mail: info.IT@saatichem.com

China

+86.21.58999113
or +86.21.58349020
e-mail: info.CN@saatichem.com

For More Information

about SaatiChem
visit our website:
www.saatiamericas.com